



# Kotak Asphalt LLP

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

Correspondence Address : Standard House,  
2nd Floor, Indira Gandhi Marg, Jamnagar 361001  
Tel.: (0288) 2553648, 2770060, 098248 50777  
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

## TEST CERTIFICATE

IS:8887:2004

Sample Batch No: 53/18

Product – Emulsion RS 1

Dt. 12/03/2018

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.02
Viscosity by Saybolt Furol viscometer at 50 deg. C	20 – 100	34
Coagulation at low temperature	Nil	Nil
Storage Stability after 24 hrs	2 % max	< 2.0 %
Particle Charge	+Ve	+Ve
Miscibility with water	No Coagulation	No Coagulation
Test on Residue		
Residue by evaporation min	60	61.2
Penetration at 25 Deg. C	80-150	110
Ductility at 27 Deg. C	50	54
Solubility in trichloroethylene (Min)	98	99.3

FOR KOTAK ASPHALT LLP



AUTHORISED SIGNATORY