



Kotak Asphalt LLP

GST – 24AAQFA2818L1Z9

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

Correspondence Address : Standard House,
2nd Floor, Indira Gandhi Marg, Jamnagar 361001
Tel.: (0288) 2553648, 2770060, 098248 50777
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

TEST REPORT

(IS 8887:2018)

Batch No.59/18

Product – Emulsion – RS 1

Date: 04/04/2018

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.03
Viscosity by Saybolt Furol viscometer At. 50 Deg. C	20-100	32
Coagulation at low temperature	Nil	Nil
Storage stability after 24 hrs.	2 % max	< 2
Particle charge	+ Ve	+ Ve
Miscibility with water	No. Coagulation	No. Coagulation
Test on residue		
Residue by evaporation min.	60	60.5
Penetration at 25 Deg. C.	80-150	92
Ductility at 27 Deg. C.	50	59
Solubility in trichloroethylene (Min.)	98	99.1

KOTAK ASPHALT LLP


TEJAL SHETH

