

Kotak Asphalt LLP

GST – 24AAQFA2818L1Z9

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

Correspondence Address : Standard House,
2nd Floor, Indira Gandhi Marg, Jamnagar 361001
Tel.: (0288) 2553648, 2770060, 098248 50777
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

TEST REPORT

(IS 8887: 2018)

Batch No.28/18

Product – Emulsion – SS 1

Dt: 02/04/2018

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.025
Viscosity by Saybolt Furol viscometer At. 25 Deg. C	20-100	82
Coagulation at low temperature	Nil	Nil
Storage stability after 24 hrs.	2 % max	< 2
Particle charge	Weak Positive	Weak Positive
Miscibility with water	Immiscible	Immiscible
Test on residue		
Residue by evaporation min.	-	-
Penetration at 25 Deg. C.	-	-
Ductility at 27 Deg. C.	-	-
Solubility in trichloroethylene, Percent by mass (Min.)	98	99.2
Distillation in percent by volume at		
190 ° C	20-55	45
225 ° C	30-75	68
260 ° C	40-90	80
190 ° C	60-100	92
Residue @ 360 Deg C Percent , Min	50	52.6
Water content percent by mass Max.	20	16.5

KOTAK ASPHALT LLP

TEJAL SHETH

