



Kotak Asphalt LLP

Correspondence Address : Standard House,
2nd Floor, Indira Gandhi Marg, Jamnagar 361001
Tel.: (0288) 2553648, 2770060, 098248 50777
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

TEST CERTIFICATE

Sample Batch No 39/18
Product – Emulsion SS 1 ASTM
Dt. 28.02.2018

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.02
Viscosity by Saybolt Furol viscometer at 25 deg. C	20 – 100	23
Coagulation at low temperature	Nil	Nil
Storage Stability after 24 hrs	1.0 % max	< 1.0 %
Particle Charge	+ Ve	+ Ve
Miscibility with water	No Coagulation	No Coagulation
Stability to mixing with cement (% coagulation) Max	2	0.24
Test on Residue from Distillation Test		
Residue by evaporation min	57	60.1
Penetration at 25 Deg. C	40 - 90	69
Ductility at 27 Deg. C	40	49.5
Solubility in trichloroethylene (Min)	97.5	99.2
Distillation Residue	57	59

FOR, KOTAK ASPHALT LLP



AUTHORISED SIGNATORY