



Kotak Asphalt LLP

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

Correspondence Address : Standard House,
2nd Floor, Indira Gandhi Marg, Jamnagar 361001
Tel.: (0288) 2553648, 2770060, 098248 50777
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

TEST CERTIFICATE

IS:8887:2004

Batch No 16/17
Product – Emulsion SS 1
Dt. 12-12-2017

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.025
Viscosity by Saybolt Furol viscometer at 25 deg. C	20 – 100	83
Coagulation at low temperature	Nil	Nil
Storage Stability after 24 hrs	2 % max	< 2
Particle Charge	Weak Positive	Weak Positive
Miscibility with water	No Coagulation	No Coagulation
Stability to mixing with cement (% coagulation) Max	2	0.2
Test on Residue from Distillation Test		
Residue by evaporation min	50	52.8
Penetration at 25 Deg. C	60-350	280
Ductility at 27 Deg. C	50	61
Solubility in trichloroethylene (Min)	98	99.5
Distillation in percent by volume at		
190 ° C	20-55	24
225 ° C	30-75	34
260 ° C	40-90	45
190 ° C	60-100	69
Water content percent by mass max	20	18.6

FOR KOTAK ASPHALT LLP



Handwritten signature

AUTHORISED SIGNATORY