



# Kotak Asphalt LLP

Plant: Village Nana Lakhya, T. Lalpur, Jamnagar Dwarka Road, Jamnagar 361 280

Correspondence Address : Standard House,  
2nd Floor, Indira Gandhi Marg, Jamnagar 361001  
Tel.: (0288) 2553648, 2770060, 098248 50777  
Fax: (0288) 2553873 Email: kmkotak@kotakgroups.com

## TEST CERTIFICATE

IS:8887:2004

Batch No 20/17

Product – Emulsion SS 2

Dt. 12-12-2017

Properties	Requirement	Result
Residue on 600 micron sieve	0.05 Max	0.025
Viscosity by Saybolt Furol viscometer at 25 deg. C	30-150	31
Coagulation at low temperature	Nil	Nil
Storage Stability after 24 hrs	2 % max	< 2
Particle Charge	Positive	Positive
Miscibility with water	No Coagulation	No Coagulation
Stability to mixing with cement (% coagulation) Max	2	0.5
Test on Residue from Distillation Test		
Residue by evaporation min	60	60.8
Penetration at 25 Deg. C	60-120	100
Ductility at 27 Deg. C	50	57
Solubility in trichloroethylene (Min)	98	99

FOR KOTAK ASPHALT LLP



AUTHORISED SIGNATORY